

Binary Alloy Phase Diagrams

Second Edition

Volume 2

Editor-in-Chief
Thaddeus B. Massalski

Editors
Hiroaki Okamoto
P.R. Subramanian
Linda Kacprzak

Publisher
William W. Scott, Jr.

Production Editor
Mary Anne Fleming

Production Assistants
Randall Boring
Amy Losasso

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the U.S. Postal Service as First Class Mail in an envelope addressed to: Commissioner of Patents, P O Box 1450, Alexandria, VA 22313.

1450 on: July 14, 2005

Name: James E. Ralston, Res. No. 34-732

Signature: [Signature]



BEST AVAILABLE COPY

Copyright © 1990
by
ASM International®
First printing, December 1990
Second printing, August 1992
Third printing, May 1996
Fourth printing, July 2001

No part of this book may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording or otherwise, without the written permission of the copyright owner.

Great care was taken in the compilation and production of this volume, but it should be made clear that no warranties, express or implied, are given in connection with the accuracy or completeness of this publication, and no responsibility can be taken for any claims that may arise.

Comments, criticisms, and suggestions are invited, and should be forwarded to ASM International, Materials Park, Ohio 44078.

The National Standard Reference Data System was established in 1963 for the purpose of promoting the critical evaluation and dissemination of numerical data of the physical, chemical, and materials sciences. The NSRDS is coordinated by the Office of Standard Reference Data of the National Institute of Standards and Technology, but involves the efforts of many groups in universities, government laboratories, and private industry. The primary aim of the NSRDS is to provide compilations of critically evaluated physical and chemical property data needed by the scientific and engineering community. Activities carried out under the NSRDS emphasize the evaluation of published data by scientists who are experts in the research areas involved.

The output of the International Data Program for Alloy Phase Diagrams, including the "Program" phase diagram evaluations contained in this compilation, has been reviewed by the Office of Standard Reference Data and accepted as a product of the National Standard Reference Data System.



Malcolm Chase, Director
Standard Reference Data
National Institute of Standards and Technology

Library of Congress Cataloging-in-Publication Data

Binary alloy phase diagrams / editor-in-chief, Theodore B. Massalski;
editors, Hiroaki Okamoto, P.R. Subramanian, Linda Kacprzak;
publisher, William W. Scott, Jr. — [2nd ed.]

p. cm.

Includes bibliographical references and index.

ISBN 0-87170-403-X (HC : set : acid free). — ISBN 0-87170-404-8

(HC : vol. 1 : acid free). — ISBN 0-87170-405-6 (HC : vol. 2 : acid free) —

ISBN 0-87170-406-4 (HC : vol. 3 : acid free)

I. Alloys. 2. Phase diagrams. I. Massalski, T.B. II. ASM International

TN690.B525 1990
669'.94—dc20

90-20749
CIP

ISBN 0-87170-403-X (set)
ISBN 0-87170-405-6 (vol. 2)
SAN: 204-7588

PRINTED IN THE UNITED STATES OF AMERICA

BEST AVAILABLE COPY

Cu-Rh, Cu-Ru, Cu-S

ments were made, the liquidus was not determined.

The Cu-Rh system is characterized by the presence of an isomorphous solid across the entire diagram in the temperature regions immediately below the solidus. The solidus determined by the incipient fusion technique appears nearly flat between approximately 25 and 50 at.% Rh. This would imply a shallow free-energy versus composition curve of the solid in corresponding composition and temperature ranges and a tendency toward formation of a miscibility gap at lower temperatures.

A single-phase continuous solid solution field exists between the components below the solidus. At still

lower temperatures, the phase field enters into a wide miscibility gap wherein it separates into two equilibrium isostructural phases, one of which is rich in Cu and the other in Rh. The critical temperature and composition of the gap are 1150 °C and 60 at.% Rh, according to [71Rau].

The miscibility gap boundary given by [71Rau] has been modified slightly in this evaluation in order to include, inside the gap, the compositions for which the X-ray showed a two-phase structure. The gap boundaries at 800 °C, according to [71Rau], are approximately at 25 and 90 at.% Rh.

The existence of a metastable single-phase continuous solid solution be-

tween (Cu) and (Rh) was established by [64Luo], based on rapid solidification of the alloys from the melt. This is in agreement with the generally accepted conditions for mutual solubility of metals in the solid state, which Cu and Rh satisfy. Transition to equilibrium phases occurred when the samples were heated at 600 °C for seven to ten days.

64Luo: H.L. Luo and P. Duwez, *J. Less-Common Met.*, **6**, 248-249 (1964).

71Rau: Ch.J. Raub, E. Röschel, D. Menzel, and M. Gadhof, *Metall.*, **25**(7), 761-762 (1971).

Published in *Bull. Alloy Phase Diagrams*, **2**(4), Mar 1982. Complete evaluation contains 1 figure, 2 tables, and 10 references.

Cu-Ru (Copper-Ruthenium)

P.R. Subramanian and D.E. Laughlin



Experimental data on the Cu-Ru system are very limited. Electrical resistivity measurements showed negligible solid solubility of Ru in (Cu) at 900 °C [32Lin]. There are no other reports on the Cu-Ru system.

The equilibrium phases of the assessed phase diagram are: (1) the liquid, L; (2) the fcc terminal solid solution, (Cu), with very limited solid solubility of Ru; and (3) the cph terminal solid solution, (Ru), with very limited solid solubility of Cu. The as-

Cu-Ru Crystal Structure Data

Phase	Composition, at.% Ru	Pearson symbol	Space group	Strukturbericht designation	Prototype
(Cu).....	0	cF4	Fm $\bar{3}$ m	A1	Cu
(Ru).....	100	hP2	P6 $\bar{3}$ /mmc	A3	Mg

assessed diagram is schematic, because it is based on a simple thermodynamic model [83Nie].

32Lin: J.O. Linde, *Ann. Physik.*, **16**, 219-248 (1932) in German.

83Nie: A.K. Niessen, F.R. de Boer, R. Boom,

P.F. de Chatel, W.C.M. Mattens, and A.R. Miedema, *Calphad*, **7**(1), 51-70 (1983).

Submitted to the APD Program. Complete evaluation contains 1 figure, 2 tables, and 4 references.

Cu-S (Copper-Sulfur)

D.J. Chakrabarti and D.E. Laughlin




Numerous studies have been conducted on the Cu-S system. Uncertainty, however, persists regarding the phase equilibria, because of the strong tendency of the sys-

tem to form several metastable phases. Marked thermomechanical history dependence is exhibited by many of these phases. For example, extreme sensitivity to applied pressure has been

known to cause a phase transformation during specimen preparation by grinding.

However, the following features have been well established. The liquid, L,



Cu-Ru



Cu-S



Cu-S Phase Diagram



Compositions in parentheses are calculated values by [80Sha].

D.J. Chakrabarti and D.E. Laughlin, 1983.

Cu-S

manifests two miscibility gaps between the liquids L_1 and L_2 above 1105 °C at Cu-rich compositions and between the liquids L_2 and L_3 above 813 °C at higher S compositions. The fcc terminal solid solution, (Cu), exhibits restricted solubility of S, amounting to 0.028 at.% at 1067 °C. The solubility of S decreases with increasing purity of Cu. The orthorhombic terminal solid solution, (S), is stable up to ~115 °C, with negligible solubility of Cu.

The monoclinic low-chalcocite (α Ch), is stable up to 103.5 ± 0.5 °C at the stoichiometric composition of Cu_2S and up to 90 ± 2 °C at 33.41 at.% S. The hexagonal high-chalcocite (β Ch) is stable from 103.5 ± 0.5 °C at the Cu-rich limit of stoichiometric Cu_2S and from 90 ± 2 °C at 33.44 at.% S up to 435 °C at 33.34 at.% S.

The fcc digenite (Dg) has a broad phase field, with the Cu-rich boundary approximately at Cu_2S stoichiometry

between 435 and 1130 ± 2 °C. The Cu-deficient boundary extends to form the defect compound $\text{Cu}_{1.98}\text{S}$, which is stable up to 507 ± 2 °C at 36.60 at.% S and down to 72 ± 3 °C at 35.65 at.% S.

The orthorhombic djurite (Dj) has the nominal composition $\text{Cu}_{1.96}\text{S}$ and is stable up to 72 ± 3 °C at $\text{Cu}_{1.984}\text{S}$ and up to 93 ± 2 °C at 33.99 at.% S. The orthorhombic compound anilite (An) of stoichiometry $\text{Cu}_{1.75}\text{S}$ (36.36 at.% S) is stable up to 75 ± 3 °C. The hexagonal

Special Points of the Cu-S System

Reaction		Composition, at.% S(Cu/S)		Temperature, °C	Reaction type
$L \leftrightarrow \text{Dg}$	(1.994)	33.40		1130 ± 2 (a)	Congruent
$L_2 \leftrightarrow L_1 + \text{Dg}$	32.9	-2.0	(2.002)	1105 (b,c,d)	Monotectic
$L \leftrightarrow (\text{Cu}) + \text{Dg}$	1.48	0.0225	(2.00025)		Eutectic
$L_2 \leftrightarrow \text{Dg} + L_3$	40.09	-36.4	99.83	818(d,e)	Monotectic
$(\text{Cu}) + \beta\text{Ch} \leftrightarrow \alpha\text{Ch}$	-0	-33.33 ± 0.02	-33.33 ± 0.02	103.5 ± 0.5 (f)	Peritectoid
$\beta\text{Ch} \leftrightarrow \alpha\text{Ch} + \text{Dj}$	33.44 ± 0.06	33.41 ± 0.02	33.78 ± 0.02	80 ± 2 (f)	Eutectoid
$(\text{Cu}) + \text{Dg} \leftrightarrow \beta\text{Ch}$	-0	33.344	33.340	435(a,g)	Peritectoid
$\text{Dg} \leftrightarrow \text{Dj} + \text{An}$	35.65 ± 0.03	34.08 ± 0.02	36.36 ± 0.04	72 ± 3 (f)	Eutectoid
$\beta\text{Ch} + \text{Dg} \leftrightarrow \text{Dj}$	33.47 ± 0.06	35.29 ± 0.03	33.99 ± 0.02	93 ± 2 (f,g)	Peritectoid
$\text{Dg} + \text{Cv} \leftrightarrow \text{An}$	38.17 ± 0.02	50.00 ± 0.02	36.36 ± 0.04	75 ± 3 (f)	Peritectoid
$\text{Dg} + L \leftrightarrow \text{Cv}$	36.60 ± 0.07	99.98	50.00 ± 0.02	507 ± 2 (a,f,g)	Peritectic
$L \leftrightarrow \text{Cv} + (\text{S})/L + \text{Cv} \leftrightarrow (\text{S})$	-100	50	-100	-115	Eutectic/peritectic

(a) From [72Cool]. (b) From [Hansen]. (c) From [80Joh]. (d) From [47Jen]. (e) From [74Rau]. (f) From [77Pot]. (g) From [66Ros].

Cu-S Crystal Structure Data

Phase	Composition, at.% S(Cu/S)	Pearson symbol	Space group	Struktur- bericht designation	Prototype
(Cu).....	-0	cF4	$Fm\bar{3}m$	A1	Cu
α chalcocite ($\alpha\text{Cu}_2\text{S}$).....	-33.33	mP144(?)	$P2_1/c$
β chalcocite ($\beta\text{Cu}_2\text{S}$).....	-33.3	hP6	$P6_3/mmc$	B82	InNi ₂
Djurite ($\text{Cu}_{1.96}\text{S}$).....	33.7 to 34.1(a)	aP380(?)	$Pmmn$ $P2_1nm(?)$ $Fmm2_1$
Digenite ($\text{Cu}_{2.4}\text{S}$).....	35.5 to 36.2(b)	cF12	$Fm\bar{3}m$	C1	CaF_2
Anilite ($\text{Cu}_{1.75}\text{S}$).....	36.36 ± 0.04	aP44(?)	$Pnma$
Covellite (CuS).....	50	hP12	$P6_3/mmc$	B18	CuS
(S).....	-100	aF128 mP48 hR6	$Fddd$ $P2_1/a$ $R\bar{3}$	A16	αS βS ϵS
Metastable phases					
Protodjurite.....	33.7 (1.97)(c) 33.8 (1.96)(d)
Tetragonal.....	33.8 (1.96)	tP12	$P4_32_12$...	Ge III(HP)
Hexagonal-tetragonal Cu_xS	34.1 to 36.4 (1.93 to 1.75)
Low digenite (αDg).....	35.84 to 36.15 (1.790 to 1.786)(e)	...	$R\bar{3}m$
Blaubleibender covellite I.....	41.7 ± 1.7 (1.4 ± 0.1)
Blaubleibender covellite II.....	47.7 ± 2.3 (1.1 ± 0.1)
CuS_2	66.67 (0.5)	...	$Pa\bar{3}(?)$

(a) At 72 °C. (b) At 80 °C. (c) At 75 °C. (d) At 93 °C. (e) At 25 °C.

Cu-S, Cu-Sb

compound covellite (Cv) of stoichiometry CuS is stable up to $507 \pm 2^\circ\text{C}$.

The assessed Cu-S phase diagram is based primarily on the work of [77Pot]. Data on much of the solidus and liquidus are derived from [72Coo]. Data on the Dg and Ch boundaries are based on the studies of [66Ros] and [72Coo]. Additionally, the work of [47Jen], [57Ruh], [58Dju], [59Oud], [60Joh], [69Mor], [70Mor], [74Rau], and [80Sha] were reviewed.

47Jen: E. Jensen, *Avhandl. Norske Videnskaps-Akad. Oslo, I. Mat.-Naturv.*, **KL**, 8, 1-14 (1947).

57Ruh: W. Ruhl and E. Saur, *Ber. Oberhess. Ges. Naturw. Heilk. Giessen, Naturw. Abt.*, **28**, 35-47 (1957) in German.

58Dju: S. Djurle, *Acta Chem. Scand.*, **12**, 1415-1428 (1958).

59Oud: J. Oudar, *Compt. Rend.*, **249**, 259-261 (1959) in French.

60Joh: F. Johannsen and H. Vollmer, *Z. Erzbergbau Metallhüttenwes.*, **13**, 313-322 (1960) in German.

66Ros: E.H. Roseboom, Jr., *Econ. Geol.*, **61**, 641-672 (1966).

69Mor: N. Morimoto, *Am. Miner.*, **54**, 1256-1268 (1969).

70Mor: N. Morimoto and K. Koto, *Am. Miner.*, **55**, (1-2), 106-117 (1970).

72Coo: W.R. Cook, Jr., *Nat. Bur. Stand. Spec. Pub.* 364, 703-712 (1972); Ph.D. thesis, Case Western Reserve University, Cleveland, OH; Gould Labs Univ. Microfilm Order No. 72-27 (1971).

74Rau: H. Rau, *J. Phys. Chem. Solids*, **35**, 1415-1424 (1974).


77Pot: R.W. Potter, II, *Econ. Geol.*, **72**(8), 1524-1542 (1977).

80Sha: R.C. Sharma and Y.A. Chang, *Metal. Trans. B*, **11**, 575-583 (1980).

Published in *Bull. Alloy Phase Diagrams*, **4**(3), Nov 1983. Complete evaluation contains 10 figures, 24 tables, and 116 references.



Enlargement of the Cu-S Diagram from 0 to 160 °C



From [77Pot].

D.J. Chakrabarti and D.E. Laughlin, 1983.



Cu-Saturated Boundary of Digenite

